



Twin Ferrule Tube Fittings Tubing Data Charts

Index

Safety Warning	Inside Front Cover
Pressure Ratings, Tubing, Gas Service	1
Maximum Working/Burst Pressures	
Copper Tubing	2
304/316 Stainless Steel Tubing	3
Alloy 6MO Tubing	4
Alloy C-276 Tubing	5
Alloy 400 Tubing	6
Grade 2 Titanium Tubing	7
Super Duplex Tubing	8
Duplex Tubing	9
Alloy 625 Tubing	10
Alloy 825 Tubing	11
Temperature Derating Factors	12
Disclaimers	Inside Back Cover

GYROLOK®



CRANE Instrumentation & Sampling, HOKE®
PO Box 4866 • Spartanburg, SC 29305-4866
(864) 574-7966 • www.hoke.com

For Your Safety

It is solely the responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. When selecting products, the total system design must be considered to ensure safe, trouble-free performance. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or property damage.

Contact your authorized HOKE® sales and service representative for information about additional sizes and special alloys.

SAFETY WARNING:

HOKE® products are designed for installation only by professional suitably qualified licensed system installers experienced in the applications and environments for which the products are intended. These products are intended for integration into a system. Where these products are to be used with flammable or hazardous media, precautions must be taken by the system designer and installer to ensure the safety of persons and property. Flammable or hazardous media pose risks associated with fire or explosion, as well as burning, poisoning or other injury or death to persons and/or destruction of property. The system designer and installer must provide for the capture and control of such substances from any vents in the product(s). The system installer must not permit any leakage or uncontrolled escape of hazardous or flammable substances. The system operator must be trained to follow appropriate precautions and must inspect and maintain the system and its components including the product(s) and at regular intervals in accordance with timescales recommended by the supplier to prevent unacceptable wear or failure.



Tubing Data Charts

Design

GYROLOK® Twin Ferrule Tube Fittings have been carefully designed for conventional compression tube fitting applications. GYROLOK® XP incorporates patented design innovations that allow the fitting to be assembled onto high yield strength and thicker wall tube.

Pressure Ratings

GYROLOK® and GYROLOK® XP fittings are rated for working pressures higher than the tubing; however, tubing should not be used above its maximum allowable working pressure.

Maximum allowable working pressures for tubing suitable for use with GYROLOK® and GYROLOK® XP are identified herein. If no pressure is identified for a given size and a wall thickness, please contact the factory for guidance as new sizes are continuously being added.

The tubing data charts show working pressure ratings which are deemed to be the maximum allowable working pressure ratings for a given alloy, size and wall thickness. The values are calculated from the allowable stress tables (S) and formulas specified in ASME B31.3, Process Piping.

Vacuum Rating

GYROLOK® offers excellent vacuum capability. With good quality tubing, GYROLOK® fittings will be leak-tight at vacuum levels of 10⁻⁹ torr while tested with a leakage sensitivity of 10⁻⁹ sccs.

Materials

GYROLOK® tube fittings are available in Brass, 316/316L, Alloy 6MO, Alloy C276, Alloy 405, Grade 5 titanium, Super Duplex, Duplex, Alloy 625, and Alloy 825. GYROLOK® XP available in 316/316L, Alloy 6MO, Alloy C276, Grade 5 Titanium, Super Duplex, Duplex, Alloy 625, and Alloy 825.

Tubing

Fully annealed tubing to the specifications identified herein are suitable for use with GYROLOK® fittings.

The tubing selected, whether metallic or nonmetallic should be compatible with the process fluid, temperature and applications. The wall thickness selections should be based on pressure and temperature conditions.

Tubing should always be fully annealed. While welded tubing may be used with GYROLOK®, inconsistencies in its manufacture and performance are sometimes encountered. As a result we recommend the use of seamless tubing.

For proper fitting performance, the tubing surface finish should be free from nicks or scratches. Do not use out of round tubing which does not easily pass through fitting components.

Fitting performance is maximized when tube ends are squarely cut, using a tubing cutter, and deburred.

Proper fitting performance demands that the fitting be significantly harder than the tubing on which it is used. Please refer to each alloy's specific tubing data charts for guidance on the recommended maximum surface hardness.

Gas Service

Gases (air, hydrogen, nitrogen, etc.) can escape through smaller leak paths than liquids. As such, the reduction of surface defects (scratches) on tubing becomes more important when the system media contains gases. As tubing wall thickness increases, the ability of the ferrules to coin out imperfections increases. The use of heavier wall tubing will help the ferrules to overcome minor surface defects that could contribute to gas leakage. HOKE recommends the following minimum wall thickness for tubing when system media contains gases.

TUBE OD (inches)	NOMINAL MINIMUM WALL THICKNESS (inches)	TUBE OD (inches)	NOMINAL MINIMUM WALL THICKNESS (inches)
1/8	0.028	3/4	0.065
3/16	0.028	7/8	0.083
1/4	0.028	1	0.083
5/16	0.035	1 1/4	0.109
3/8	0.035	1 1/2	0.134
1/2	0.049	2	0.180

Suggested Allowable Pressure Tables

Figures and tables are for reference only. HOKE makes no implication that these values can be used for design work. Applicable codes and practices in industry should be reviewed and considered. ASME Codes are the successor to and replacement of ASA Piping Codes. For combinations not shown, consult factory.

For Welded Tubing

For welded tubing, a derating factor must be applied for weld integrity.

- 1) For double-welded tubing, multiply working pressure by 0.85.
- 2) For single-welded tubing, multiply working pressure by 0.80.

CAUTION: Limited test data is available on certain alloys and sizes due to tubing availability. Please consult factory for further guidance.

GYROLOK®



Tube Data Charts

Copper Annealed Seamless Tubing

ASTM B-75 or Equivalent, Maximum Recommended Hardness HR^F 55

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 6,000 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 6,000 psi (41.3 MPa).

For gas service, select a wall thickness that is not shaded (see Gas Service on page 1).

TUBING O.D. (inch)	WALL THICKNESS (inch)											
	0.014	0.020	0.028	0.032	0.035	0.049	0.065	0.083	0.095	0.109	0.120	
	WORKING PRESSURE (psig)											
1/16	2800	4000										
1/8			2800	3300	3700							
3/16			1800	2100	2300	3400						
1/4			1300	1500	1600	2400	3400					
3/8				900	1000	1500	2100	2800				
1/2					700	1100	1500	2000				
5/8					600	800	1200	1500	1800			
3/4					500	700	900	1200	1500	1700		
1					300	500	700	900	1100	1200	1400	

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 41.3 MPa between -29° C and 38° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 6,000 psi (41.3 MPa).

For gas service, select a wall thickness that is not shaded (see Gas Service on page 1).

TUBING O.D. (mm)	WALL THICKNESS (mm)					
	0.8	1	1.5	2	2.5	3
	WORKING PRESSURE (barg)					
3	240					
4	170	220				
6	100	140	220			
8	80	100	160			
10	60	80	120	170		
12	50	60	100	140		
14		50	80	110	150	
15		50	80	100	140	
16		40	70	100	130	160

Ordering Information

High quality, fully annealed seamless tubing, ASTM B75 and EN 1057 or equivalent. Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

304 & 316 Stainless Steel Annealed Seamless Tubing

ASTM A-269 UNS S30400 & S31600 or Equivalent, Maximum Recommended Hardness HR^B 90

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 20,000 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 20,000 psi (137.9 MPa). Values shown below are for seamless annealed tubing only.

For gas service, select a wall thickness that is not shaded (see Gas Service on page 1).

Tubing is suitable for use with either 316 stainless steel or Alloy 6MO GYROLOK[®] fittings.

TUBING O.D. (inch)	WALL THICKNESS (inch)													
	0.010	0.020	0.028	0.035	0.049	0.065	0.083	0.095	0.109	0.120	0.134	0.156	0.165	0.188
	WORKING PRESSURE (psig)													
1/16	5600	12000												
1/8			8500	10900										
3/16			5400	7000	10200	13800	17300							
1/4			4000	5100	7500	10200	13300 _{XP}	15200 _{XP}						
3/8				3000	4800	6500	8600							
1/2				2600	3700	5100	6700	7800 _{XP}	8800 _{XP}	9800 _{XP}	11000 _{XP}	13000 _{XP}	13800 _{XP}	15600 _{XP}
5/8					2900	4000	5200	6000	7100					
3/4					2400	3300	4200	4900	5800	6400	7300 _{XP}	8100 _{XP}		
1						2400	3100	3600	4200	4700	5300	6200 _{XP}	6700 _{XP}	7700 _{XP}
1 1/4							2400	2800	3300 _{XP}	3600 _{XP}	4100 _{XP}	4900 _{XP}		
1 1/2								2300	2700	3000	3400 _{XP}	4000 _{XP}	4200 _{XP}	4900 _{XP}
2										2200	2500	2900	3100 _{XP}	3600 _{XP}

Where there is an XP suffix, then only GYROLOK[®] XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 137.9 MPa between -29° C and 38° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 20,000 psi (137.9 MPa). For gas service, select a wall thickness that is not shaded (see Gas Service on page 1).

GYROLOK[®]-XP fittings are intended for use where pressures are indicated with the “XP” subscript.

Tubing is suitable for use with either 316 stainless steel or Alloy 6MO GYROLOK[®] fittings.

TUBING O.D. (mm)	WALL THICKNESS (mm)										
	0.8	1	1.2	1.5	1.8	2	2.2	2.5	3	3.5	4.0
	WORKING PRESSURE (barg)										
3	710	900									
4	520	660									
6	330	430	520	670	820 _{XP}	920 _{XP}					
8		310	380	490							
10		240	300	380	470	530	590 _{XP}	680 _{XP}	830 _{XP}		
12		200	240	310	380	430	480 _{XP}	560 _{XP}	680 _{XP}		
14		180	220	280	340	390					
15		170	200	260	320	360					
16			190	240	300	330					
18			170	210	260	290	330	380			
20			150	190	230	260	290	330			
22				170	210	230	260	300			
25					180	200	230	260	320 _{XP}		
30						170	190	210	260	310	
32							160	200	240	290	330
38								170	200	240	280

Where there is an XP suffix, then only GYROLOK[®] XP will work with this wall thickness.

Ordering Information

High quality, fully annealed (Type 304, 304/304L, 316, 316/316L, 317/317L) seamless tubing, ASTM A269 or A213 equivalent. Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Alloy 6MO Super Austenitic Stainless Steel

ASTM A-269, A-213, UNS S31254 or Equivalent, Maximum Recommended Hardness HR^B 90

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 27,100 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 27,100 psi (186.9 MPa).

For gas service, select a wall thickness that is not shaded (see Gas Service on page 1).
Tubing is suitable for use with either 316 stainless steel or Alloy 6MO GYROLOK® fittings.

TUBING O.D. (inch)	WALL THICKNESS (inch)								
	0.028	0.035	0.049	0.065	0.083	0.095	0.109	0.120	0.134
	WORKING PRESSURE (psig)								
1/8	11500								
1/4		6900	10100	13900 _{XP}					
3/8		4500	4500	8900	11700 _{XP}				
1/2		3500	5000	6900	9000				
5/8			4000	5400	7100				
3/4			3300	4400	5800				
1				3300	4200	4900 _{XP}	5700 _{XP}		
1 1/4						3900 _{XP}	4500 _{XP}		
1 1/2							3700 _{XP}	3700 _{XP}	4600 _{XP}

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 186.9 MPa between -29° C and 38° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 186.9 MPa (27,100 psi).

For gas service, select a wall thickness that is not shaded (see Gas Service on page 1).
Tubing is suitable for use with either 316 stainless steel or Alloy 6MO GYROLOK® fittings.

TUBING O.D. (mm)	WALL THICKNESS (mm)										
	0.8	1	1.2	1.5	1.8	2	2.2	2.5	3	3.5	4
	WORKING PRESSURE (barg)										
3	960	1220									
6	410	580	710	910							
8		420									
10		330	400	520	640	720					
12		270	330	420	520	590					
16			260	330	400	450					
18			230	290	350	400					
20			200	260	320	350	390	450			
25					250	280	310	360	430 _{XP}	520 _{XP}	600 _{XP}
30									360 _{XP}	420 _{XP}	490 _{XP}
38									270 _{XP}	320 _{XP}	380 _{XP}

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Ordering Information

High quality, fully annealed Alloy 6MO tubing, ASTM A269 or equivalent. Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Alloy C-276 Solution Annealed Seamless Tubing

ASTM B622 UNS N10276 or Equivalent, Maximum Recommended Hardness HRB 98

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 27,300 psi between -20° F and 400° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 27,300 psi (188.2 MPa).

TUBING O.D. (inch)	WALL THICKNESS (inch)						
	0.010	0.014	0.028	0.035	0.049	0.065	0.083
WORKING PRESSURE (psig)							
1/16	7600	11100					
1/8			11600	14800			
1/4			5500	7000	10200		
3/8				4500	6500	8900	
1/2				3500	5100	6900	9100 _{XP}
5/8					4000		
3/4					3300	4500	
1						3300	

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 188.2 MPa psi between -29° C and 204° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 188.2 MPa (27,300 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)		
	1.0	1.5	2.0
WORKING PRESSURE (barg)			
3	1230		
6	580	920 _{XP}	
8	420		
10	330	520	
12	270	430	590 _{XP}
18		290	400
20		260	
25		210	280

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Ordering Information

High quality, fully seamless alloy C-276 tubing, ASTM B622 or equivalent. Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Alloy 400 (Nickel-Copper) Annealed Seamless Tubing

ASTM B-165 UNS N04400 or Equivalent, Maximum Recommended Hardness HRB 75

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 18,700 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 18,700 psi (128.9 MPa).

TUBING O.D. (inch)	WALL THICKNESS (inch)					
	0.010	0.028	0.035	0.049	0.065	0.083
	WORKING PRESSURE (psig)					
1/16	5200					
1/8		7900	10200			
1/4		3700	4800	7000		
3/8			3100	4400		
1/2			2400	3500	4700	6200
5/8				2700	3700	
3/4				2200	3000	
1					2200	

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 128.9 MPa psi between -29° C and 38° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 128.9 MPa (18,700 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)			
	0.8	1	1.2	1.5
	WORKING PRESSURE (barg)			
6	310	400		
8		290		
10		230	280	360
12		190	230	290

Ordering Information

High quality, fully annealed seamless alloy 400 hydraulic tubing, ASTM B165 or equivalent.
Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Grade 2 Titanium Annealed Seamless Tubing

ASTM B-338 UNS R50400 or Equivalent, Maximum Recommended Hardness HRB 90

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 16,700 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 16,700 psi (115.1 MPa). For working pressure in accordance with ASME B31.1, multiply by 0.85.

TUBING O.D. (inch)	WALL THICKNESS (inch)			
	0.028	0.035	0.049	0.065
	WORKING PRESSURE (psig)			
1/8		9100	12800	
1/4	3300	4200	3200	8500
3/8		2700	4000	5400
1/2		2100	3100	4200
3/4			2000	2700
1			1500	2000

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 115.1 MPa psi between -29° C and 38° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 115.1 MPa (16,700 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)									
	0.8	1	1.2	1.5	1.8	2.0	2.5	3.0	3.5	4.0
	WORKING PRESSURE (barg)									
6	280	350	440	560						
10		200	250	320	390	440				
12		170	200	260	320	360	460			
14				230	290	320				
16				200						
18				180	220 _{xp}	240 _{xp}				
20						220	280	340	410 _{xp}	460 _{xp}
25				120	150	170				

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Ordering Information

High quality, fully annealed seamless grade 2 titanium, ASTM B338 or equivalent.

Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Super Duplex Stainless Steel

ASTM A789 UNS S32750 or Equivalent, Maximum Recommended Hardness HRC 32

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 38,700 psi between -20° F and 200° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 38,700 psi (267 MPa).

TUBING O.D. (inch)	WALL THICKNESS (inch)						
	0.035	0.049	0.065	0.083	0.095	0.109	0.120
	WORKING PRESSURE (psig)						
¼	9900	14500 _{XP}	19800 _{XP}				
⅜	6400	9200	12700 _{XP}				
½	5000	7200	9800	12900 _{XP}	15100 _{XP}		
¾		4700	6300	8300	9600 _{XP}	11200 _{XP}	12500 _{XP}
1			4700	6100 _{XP}			

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 250.3 MPa psi between -29° C and 93° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 267 MPa (38,700 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)			
	1.0	1.2	1.5	2.0
	WORKING PRESSURE (barg)			
6	600/830 _{XP} ¹			
10	480	580	740	
12	390	480	610	
18	270	330	420	570 _{XP}
20	240	290	370	510 _{XP}
25			290	400 _{XP}

NOTE 1: standard Gyrolok is rated 600 barg. -XP is rated 830 barg.

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Ordering Information

High quality, fully annealed seamless 2507 super duplex tubing, ASTM A789 or equivalent.

Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Duplex Stainless Steel

ASTM A789 UNS S31803 or Equivalent, Maximum Recommended Hardness HRC 30.5

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 30,000 psi between -20° F and 200° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 30,000 psi (206.8 MPa).

TUBING O.D. (inch)	WALL THICKNESS (inch)				
	0.035	0.049	0.065	0.083	0.095
	WORKING PRESSURE (psig)				
¼	7700	11200 _{XP}	15400 _{XP}		
⅜	5000	7200	9800 _{XP}		
½		5600	7600	10000 _{XP}	
¾		3600	4900	6400 _{XP}	7400 _{XP}
1			3600	4700 _{XP}	

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 206.8 MPa psi between -20° C and 93° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 206.8 MPa (30,000 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)				
	0.8	1	1.2	1.5	2
	WORKING PRESSURE (barg)				
6	500	640			
10		370	450	570	
12		300	370	470	
18				320	440
20				290	390
25				230	310

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Ordering Information

High quality, fully annealed seamless 2205 duplex tubing, ASTM A789 or equivalent.

Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Alloy 625 Nickel -Chromium-Molybdenum Alloy

ASTM B-444 UNS N06625 Grade 2 or Equivalent

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 26,700 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 26,700 psi (184.1 MPa).

TUBING O.D. (inch)	WALL THICKNESS (inch)				
	0.035	0.049	0.065	0.083	0.095
	WORKING PRESSURE (psig)				
³ / ₁₆	9400				
¹ / ₄	6800	10000	13700 _{XP}		
³ / ₈	4400	6400	8700	11500 _{XP}	
¹ / ₂	3500	5000	6800	8900	10400 _{XP}
³ / ₄		3200	4400		

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 184.1 MPa psi between -28° C and 37° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 184.1 MPa (26,700 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)		
	1.0	1.2	1.5
	WORKING PRESSURE (barg)		
6	570		
10	330	400	510
12	270	330	420

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Ordering Information

High quality, fully annealed seamless alloy 625 tubing, ASTM B444 or equivalent.

Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Tubing Data Charts

Alloy 825 Nickel-Iron-Chromium Alloy

ASTM B-423 UNS N08825 or Equivalent

Maximum Working Pressure (psi) for Fractional Sizes

Allowable Stress = 23,300 psi between -20° F and 100° F

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 23,300 psi (160.6 MPa).

TUBING O.D. (inch)	WALL THICKNESS (inch)			
	0.035	0.049	0.065	0.083
WORKING PRESSURE (psig)				
1/8	12700			
3/16	8200			
1/4	5900	5700	11900	
3/8	3800	5500	7300	
1/2	3000	4300	5900	
3/4			3800	5000
1			2800	3600

Where there is an XP suffix, then only GYROLOK® XP will work with this wall thickness.

Maximum Working Pressure (bar) for Metric Sizes

Allowable Stress = 160.6 MPa psi between -29° C and 38° C

Allowable working pressures are calculated based on equations from ASME B31.1 and ASME B31.3 for a maximum allowable stress (S) of 160.6 MPa (23,300 psi).

TUBING O.D. (mm)	WALL THICKNESS (mm)		
	1	1.2	1.5
WORKING PRESSURE (barg)			
6	500		
10	280	350	440
12	230	280	360

Ordering Information

High quality, fully annealed seamless alloy 825 tubing, ASTM B423 or equivalent.

Tubing to be free of scratches and suitable for bending. Secondary mechanical finishing is prohibited.

Maximum Allowable Pressure Derating Factors, Elevated Temperatures

(Multiply value in Tubing Date Chart by value in Chart Below)

Temperature °F	100	200	300	400	500	600	650	700	750	800	850	900	950	1000	1050	1100	1150	1200	1250
Temperature °C	38	93.33	148.9	204.4	260	315.6	343.3	371.1	398.9	426.7	454.4	482	510	538	566	593	621	649	677
316 Stainless Steel	—	—	—	0.97	0.90	0.85	0.84	0.82	0.81	0.80	0.79	0.78	0.77	0.77	0.73	0.62	0.49	0.37	0.28
Alloy 6MO	—	—	—	0.95	0.86	0.82	0.81	0.80	0.80	0.79	0.79	—	—	—	—	—	—	—	—
Alloy C276	—	—	—	—	0.99	0.92	0.90	0.88	0.86	0.85	0.84	0.83	0.82	0.81	0.68	0.55	0.45	0.36	0.29
Alloy 400	—	0.88	0.81	0.79	0.79	0.79	0.79	0.78	0.78	0.76	0.59	0.43	—	—	—	—	—	—	—
Titanium	—	0.93	0.868	0.80	0.72	0.67	0.67	0.62	0.57	0.53	0.49	0.46	—	—	—	—	—	—	—
Super Duplex	—	0.99	0.94	0.91	0.88	0.88	—	—	—	—	—	—	—	—	—	—	—	—	—
Duplex	—	—	0.96	0.93	0.91	0.90	—	—	—	—	—	—	—	—	—	—	—	—	—
Alloy 625	—	—	0.99	0.98	0.97	0.95	0.94	0.93	0.92	0.91	0.90	0.90	0.89	0.78	0.78	0.58	0.53	0.33	—
Alloy 825	—	—	—	—	—	—	—	—	0.99	0.99	0.98	0.98	0.97	0.96	—	—	—	—	—
Monel	—	0.81	0.81	0.79	0.78	0.78	0.78	0.78	0.77	0.76	0.66	0.48	—	—	—	—	—	—	—

EXAMPLE:	
Alloy	316 Stainless Steel
Temperature	500° F
Tube Size	1/2" x .065"
MAWP from Chart	5100 psig
New MAWP	MAWP * Derate Factor
New MAWP	5100 * .90
New MAWP	4590 psig



The Small Bore Instrumentation Specialists



We specialize in small bore instrumentation products up to 2" that deliver benchmark performance quality & safety; provide the broadest array of superior alloy offerings in the market; decades of proven success in a wide range of industries; a roster of "who's who" customers & projects globally; original "Best Solution" engineering & designs; and are focused on continuous improvement in all aspects of our business.

Proudly Distributed By:



CRANE INSTRUMENTATION & SAMPLING Inc.
405 Centura Ct.
Spartanburg, SC 29305, USA
Tel: 1-864-574-7966
PO Box 4866, Spartanburg, SC 29305-4866 USA

Crane Co., and its subsidiaries cannot accept responsibility for possible errors in catalogues, brochures, other printed materials, and website information. Crane Co. reserves the right to alter its products without notice, including products already on order provided that such alteration can be made without changes being necessary in specifications already agreed. All trademarks in this material are the property of the Crane Co. or its subsidiaries. The Crane and Crane brands logotype (CENTER LINE®, COMPAC-NOZ®, CRANE®, DEPA® & ELRO®, DOPAK®, DUO-CHEK®, FLOWSEAL®, GYROLOK®, GO REGULATOR®, HOKE®, JENKINS®, KROMBACH®, NOZ-CHEK®, PACIFIC VALVES®, RESISTOFLEX®, REVO®, SAUNDERS®, STOCKHAM®, TEXAS SAMPLING®, TRIANGLE®, UNI-CHEK®, VALVES®, WTA®, and XOMOX®) are registered trademarks of Crane Co. All rights reserved.